



**Europäisches  
Patentamt**

**European  
Patent Office**

**Office européen  
des brevets**

**Bescheinigung**

**Certificate**

**Attestation**

Die angehefteten Unterla-  
gen stimmen mit der  
ursprünglich eingereichten  
Fassung der auf dem näch-  
sten Blatt bezeichneten  
europäischen Patentanmel-  
dung überein.

The attached documents  
are exact copies of the  
European patent application  
described on the following  
page, as originally filed.

Les documents fixés à  
cette attestation sont  
conformes à la version  
initialement déposée de  
la demande de brevet  
européen spécifiée à la  
page suivante.

**Patentanmeldung Nr. Patent application No. Demande de brevet n°**

03447234.0

Der Präsident des Europäischen Patentamts;  
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets  
p.o.

R C van Dijk

**BEST AVAILABLE COPY**



Anmeldung Nr:  
Application no.: 03447234.0  
Demande no:

Anmeldetag:  
Date of filing: 24.09.03  
Date de dépôt:

Anmelder/Applicant(s)/Demandeur(s):

SIDMAR N.V.  
John Kennedylaan 51  
B-9042 Gent  
BELGIQUE

Bezeichnung der Erfindung/Title of the invention/Titre de l'invention:  
(Falls die Bezeichnung der Erfindung nicht angegeben ist, siehe Beschreibung.  
If no title is shown please refer to the description.  
Si aucun titre n'est indiqué se référer à la description.)

A method for the production of metal coated steel products

In Anspruch genommene Priorität(en) / Priority(ies) claimed / Priorité(s)  
revendiquée(s)  
Staat/Tag/Aktenzeichen/State/Date/File no./Pays/Date/Numéro de dépôt:

Internationale Patentklassifikation/International Patent Classification/  
Classification internationale des brevets:

G23C/

Am Anmeldetag benannte Vertragstaaten/Contracting states designated at date of  
filing/Etats contractants désignées lors du dépôt:

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IT LU MC NL  
PT RO SE SI SK TR LI

## A METHOD FOR THE PRODUCTION OF METAL COATED STEEL PRODUCTS

### 10 Field of the invention

[0001] The present invention is related to the production of metal coated steel products, in particular galvanized or aluminized products, or products having Zn-Al coatings, wherein an additional alloying element such as  
15 magnesium is added to the coating, in order to improve the corrosion resistance.

### State of the art

[0002] The best known way of improving the corrosion  
20 resistance of steel products is by providing a metallic coating, such as a Zn-coating or an Al-coating. Combined Zn-Al alloy hot dip coated steel sheets, such as Zn + 5% Al (Galfan) and Zn + 55% Al + 1.6% Si (Galvalume) have been developed. These have a higher corrosion resistance than  
25 galvanized steel due to having both the corrosion prevention ability of Zn and the passivation ability of Al.

[0003] Apart from Al, Mg is also known to have a beneficial effect on corrosion resistance. In particular, the effect of Mg in Zn-Al hot dip coated steel sheet has  
30 been proven. Several coatings containing Mg in addition to Zn and Al with improved corrosion resistance have been developed and commercialized. Most of these coatings are produced by bath alloying in the hot dip galvanizing process.

[0004] Another approach to produce Mg-alloyed metallic coatings is to start from a hot dip metallic coating (e.g. galvanized Zn-Al or aluminized Al-Si coating) or electrolytically galvanized Zn, and add Mg on top of the coating by means of Physical Vapour Deposition, followed by a thermal treatment in order to diffuse the Mg in the coating and make a Mg-alloyed coating. In that case a thin Mg layer (usually less than 1  $\mu\text{m}$ ) is deposited under vacuum. Afterwards this two-layer coating system is diffusion-annealed. In this thermal treatment the Mg diffuses into the metallic coating and forms intermetallic compounds (e.g.  $\text{MgZn}_2$ ,  $\text{Mg}_2\text{Zn}_{11}$ ). As a result the metallic coating is composed of an alloyed coating on top of the conventional metallic coating or of a metallic coating with intermetallic compounds throughout the whole thickness. This last technique is known for example from document WO-A-0214573, wherein the coating is produced by vacuum deposition of Mg on a Zn-coating, followed by induction heating under protective atmosphere ( $\text{HNx}$ ,  $\text{N}_2$ , He or Ar).

[0005] The disadvantage of induction heating is that the heating works from the inner side of the galvanized steel substrate. This results in the fact that there is a risk of galvannealing the Zn-coating, i.e. risking the occurrence of a Fe-Zn reaction. This phenomenon is somewhat delayed in the case of a hot dip galvanised coating, wherein the galvannealing requires the breakdown of the  $\text{Fe}_2\text{Al}_3$  inhibition layer to form Fe-Zn intermetallic compounds. However in the case of an electrogalvanized substrate, the Fe-Zn reaction starts even earlier as there is no Fe-Al intermetallic layer present at the interface steel/zinc. The result of this Fe-Zn reaction is mainly a loss in ductility of the coating.

[0006] In the case of Mg-deposition, it is required to clean and activate the coating surface prior to the deposition. In particular, an oxide layer needs to be removed from the surface of hot dip galvanized or  
5 aluminized products in order to allow the Mg diffusion into the metallic coating, or a skin pass emulsion may have to be removed in case the Mg-addition takes place after a skin pass, i.e. a hardening rolling step. According to the prior art, this may be done by the process of alkaline  
10 degreasing, which is however not a compact process, in the sense that such a degreasing step requires a large physical space in the production line, which is undesirable in terms of efficiency and cost.

#### 15 Aims of the invention

[0007] The present invention aims to provide a method for the production of metal coated steel products, wherein the coating is applied by hot dip coating or electrolytic coating, mainly galvanizing or aluminizing,  
20 followed by a deposition of an additional metallic element, preferably Mg. In the first place, the method of the invention aims to allow a more compact production process, compared to the prior art, as well as a heating step which does not cause the Fe-Zn reaction to take place.

25

#### Summary of the invention

[0008] The present invention is related to a method for the production of metal coated steel products, comprising the steps of :

- 30
- providing a steel product with a metallic coating,
  - adding an additional metallic element to said coating,
  - subjecting said product to a thermal treatment,
- characterized in that :

- prior to the addition of said additional element, said product is subjected to a plasma treatment, for cleaning and activating the surface of said coating,
- said additional element is added through a physical vapour deposition technique,
- said thermal treatment is applied by directing high energy infra red radiation towards the outer surface of said coating.

[0009] According to the preferred embodiment, said metallic coating is chosen from the group consisting of : a Zn-coating, an Al-coating, a Zn-Al coating.

[0010] Preferably, said additional metallic element is Mg, and said Mg is added through sputtering or evaporation under low pressure.

[0011] According to the preferred embodiment, said plasma treatment is a Dielectric Barrier Discharge (DBD) plasma treatment, taking place at a pressure of between 0.1bar and 1bar, under an atmosphere consisting of N<sub>2</sub> or of a mixture of N<sub>2</sub> and H<sub>2</sub>. Alternatively, said plasma treatment may take place under vacuum.

[0012] The method of the invention is preferably applied to a steel sheet.

[0013] Further according to the invention, said thermal treatment may be given under an inert atmosphere or under air.

[0014] The invention is equally related to an apparatus for performing the method of the invention, said apparatus comprising :

- a means for performing a plasma treatment on a metal coated product,
- a means for adding an additional element to said coating by using a physical vapour deposition technique,

- a means for directing high energy infra red radiation towards the outer surface of said coating.

#### Detailed description of the invention

- 5 [0015] The method of the invention comprises the following steps, to be performed on a metal coated steel product, preferably a steel sheet which has undergone a hot dip metal coating or electrolytic coating process step :
- cleaning and activating the surface of the coating by
  - 10 - subjecting said product to a plasma treatment.
  - Depositing an additional metallic element onto said surface by a physical vapour deposition technique, such as sputtering or evaporation.
  - Subjecting said product to a thermal treatment by
  - 15 - applying high energy infra red radiation directed at the coated side of the product.

- [0016] In the preferred embodiment, the metallic coating consists of a Zn-coating, an Al-coating or a Zn-Al coating, applied by hot dip galvanizing/aluminizing or (in
- 20 the case of a Zn-coating) electrolytic galvanizing, while the added metallic element is Mg.

- [0017] According to the invention, the plasma treatment step may take place under vacuum. According to the preferred embodiment however, the plasma treatment is a
- 25 Dielectric Barrier Discharge plasma treatment, taking place under atmospheric or slightly lower pressure, in practice between 0.1 and 1 bar. In this case, the atmosphere under which the plasma treatment takes place consists of  $N_2$  or of a mixture of  $N_2$  and  $H_2$ . Any one of two
- 30 known configurations for the DBD plasma treatment can be applied, namely the parallel plate configuration and the remote plasma configuration. In the first case the substrate is the second electrode and thus the sheet is

treated in the plasma itself. In the second case the sheet is treated by the afterglow of the plasma.

[0018] Details about plasma techniques can be found in one or more of the following documents : US-A-6 051 150,  
5 US-A-6 004 631, WO-A-96/38311, US-A-5 669 583, DE-A-195 46 187, EP-A-0 467 639, WO-A-01/38596, US-A-5 384 167.

[0019] The physical vapour deposition of Mg onto the coating is performed at low pressure or under vacuum, e.g. by evaporation or sputtering. Evaporation is a technique  
10 that allows for higher deposition rates and thus higher line speeds, which are especially favourable if the configuration is installed on an existing electrogalvanizing or hot dip galvanizing/aluminizing line.

[0020] According to the invention, the steel product  
15 is then subjected to a thermal treatment, by using high energy infra red radiation directed at the coating. This may be performed by a series of high energy infra red lamps, similar to the configurations which are known in the production of painted metal sheets (ref. EP-A-1201321).  
20 Preferably, high energy infra red radiation is applied with an energy density of  $400\text{kW/m}^2$  or more. The advantage of this type of heating, apart from its speed, is the fact that the steel product is heated from the outside. Consequently, the Mg-diffusion into the Zn or Al coating  
25 starts easier from the surface without affecting the interface between the steel substrate and the Zn- or Al coating. The use of high energy infra red for the thermal treatment of metal coated products is not known so far, which is mainly due to the fact that without the additional  
30 Mg-addition, the aspect of the coatings is more reflective, which would not allow the radiation to be absorbed in a sufficient manner for the required heating to take place. The deposited Mg lends a non-reflective aspect to the



coating, allowing an efficient heat absorption when applying the high energy infra red.

[0021] According to the invention, the high energy infra red treatment may take place under (air) atmospheric conditions, or in the presence of an inert gas. The latter alternative provides the advantage that the temperature at the end of the deposition step is less critical, given that in inert circumstances there is no danger of oxide formation, when the temperature exceeds a given limit.

10 [0022] Because of the application of the plasma treatment and of the high energy infra red heating, the method of the invention is much more compact, i.e. it requires less physical space than prior art processes, which allows it to be incorporated into existing metal  
15 coating production lines more easily.

CLAIMS

1. A method for the production of metal  
5 coated steel products, comprising the steps of :

- providing a steel product with a metallic coating,
- adding an additional metallic element to said coating,
- subjecting said product to a thermal treatment,

characterized in that :

- 10 - prior to the addition of said additional element, said product is subjected to a plasma treatment, for cleaning and activating the surface of said coating,
- said additional element is added through a physical vapour deposition technique,
- 15 - said thermal treatment is applied by directing high energy infra red radiation towards the outer surface of said coating.

2. The method according to claim 1, wherein said metallic coating is chosen from the group consisting  
20 of : a Zn-coating, an Al-coating, a Zn-Al coating.

3. The method according to claim 1 or 2, wherein said additional metallic element is Mg, and wherein said Mg is added through sputtering or evaporation under low pressure.

25 4. The method according to any one of claims 1 to 3, wherein said plasma treatment is a Dielectric Barrier Discharge (DBD) plasma treatment, taking place at a pressure of between 0.1bar and 1bar, under an atmosphere consisting of N<sub>2</sub> or of a mixture of N<sub>2</sub> and H<sub>2</sub>.

30 5. The method according to any one of claims 1 to 3, wherein said plasma treatment takes place under vacuum.

6. The method according to any one of claims 1 to 5, wherein said product is a steel sheet.

7. The method according to any one of claims 1 to 6, wherein said thermal treatment is given under an inert atmosphere.

8. The method according to any one of claims 1 to 6, wherein said thermal treatment is given under air.

9. Apparatus for performing the method of any one of claims 1 to 8, comprising :

- 10 - a means for performing a plasma treatment on a metal coated product,
- a means for adding an additional element to said coating by using a physical vapour deposition technique,
- a means for directing high energy infra red radiation
- 15 towards the outer surface of said coating.

ABSTRACTA METHOD FOR THE PRODUCTION OF METAL COATED STEEL PRODUCTS

5

The present invention is related to a method for the production of metal coated steel products, comprising the steps of :

- providing a steel product with a metal coating,
- 10 - adding an additional metallic element to said coating,
- subjecting said product to a thermal treatment, characterized in that :
- prior to the addition of said additional element, said product is subjected to a plasma treatment via a
- 15 dielectric barrier discharge, for cleaning and activating the surface of said coating,
- said additional element is added through a physical vapour deposition technique,
- said thermal treatment is applied by directing high
- 20 energy infra red radiation towards the outer surface of said coating.

# **Document made available under the Patent Cooperation Treaty (PCT)**

International application number: PCT/EP04/010673

International filing date: 23 September 2004 (23.09.2004)

Document type: Certified copy of priority document

Document details: Country/Office: EP  
Number: 03447234.0  
Filing date: 24 September 2003 (24.09.2003)

Date of receipt at the International Bureau: 23 December 2005 (23.12.2005)

Remark: Priority document submitted or transmitted to the International Bureau but not  
in compliance with Rule 17.1(a) or (b)



World Intellectual Property Organization (WIPO) - Geneva, Switzerland  
Organisation Mondiale de la Propriété Intellectuelle (OMPI) - Genève, Suisse

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☒ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**